

**BLAKELY  
SOKOLOFF  
TAYLOR &  
ZAFMAN LLP**

12400 Wilshire Boulevard, Seventh Floor  
Los Angeles, California 90025-1026  
Telephone: (310) 207-3800  
Facsimile: (310) 820-5988 or 820-5270

## FACSIMILE TRANSMITTAL SHEET

**Deliver To:** Examiner Mark Ruthkowsky  
**Company:** U.S. Patent and Trademark Office  
**Fax No.:** (703) 872-9725  
**From:** William Hickman  
**Date:** December 19, 2002  
**Time:** \_\_\_\_\_  
**Number of Pages:** 2 (Including Cover Sheet)  
**Operator:** Nadya Gordon  
**Our Reference:** Docket No. 003364.P020

<b>SUBJECT:</b>	<u>Serial No. 09/363,578; filed 7/29/1999</u>
<b>REMARKS:</b>	<u>Please see attached which is provided for your reference for the interview with Will Hickman that is scheduled for Monday, 12/23/02, at 11:00am (EST).</u>

CONFIDENTIALITY NOTE: The documents accompanying this facsimile transmission contain information from the law firm of Blakely, Sokoloff, Taylor & Zafman which is confidential or privileged. The information is intended to be for the use of the individual or entity named on this transmission sheet. If you are not the intended recipient, be aware that any disclosure, copying, distribution or use of the contents of this faxed information is prohibited. If you have received this facsimile in error, please notify us by telephone immediately so that we can arrange for the retrieval of the original documents at no cost to you.

If you do not receive all the pages, or if there is any difficulty in receiving, please call: (310) 207-3800 and ask for the operator named above.

Serial #  
09/363,578

VERSION WITH MARKINGS TO SHOW CHANGES MADE

IN THE CLAIMS

The claims are amended as follows.

1. (Six Times Amended) A carbonaceous active material comprising:  
at least one crystalline graphite core; and  
an amorphous graphitizable carbon shell coating the outside of the crystalline graphite core wherein a differential thermal analysis conducted on the carbonaceous active material in 10°C increments per minute starting from room temperature and proceeding to 1000°C at atmospheric pressure results in the displaying of at least two exothermic peaks overlapping to form shoulders, and  
~~the amorphous graphitizable carbon shell coating is derived from an amorphous carbon precursor selected from the group consisting of coal pitch, petroleum pitch, coal-based oil, and heavy oil wherein the carbonaceous active material is prepared by a~~  
process comprising:  
dissolving amorphous carbon in an organic solvent to produce a solution;  
mixing crystalline graphite particles with the solution;  
refluxing the mixture;  
filtering the mixture to obtain a powder; and  
heat treating the powder at approximately 1000°C to obtain the active  
material.

pg. 4, lines 6